

Humimic Medical Gelatin

Synthetic Gelatin for Simulating Tissue

Humimic Medical's gelatin is 100% synthetic, and durability and shape retention are varied between gelatin types to closely mimic a range of tissues. Humimic Medical gelatin is completely stable at room temperature, and it will not dehydrate over time. Humimic Medical synthetic gelatin is naturally clear but is dyable to create completely customizable phantoms. Humimic Medical gelatin is also odorless, non-toxic, and moldable into any shape. Humimic Medical gelatin has self-healing properties - it can endure many needle punctures before melting and remolding is necessary. Humimic Medical gelatin is compatible with ultrasound, CT scans, and MRIs, making it ideal for use as a tissue model.



Prepared 06. 05. 2020
Reviewed 01 06. 08. 2020



Material Properties Data

Gelatin Type	Young's Modulus (Pa)	Shore Rating (00)	Density (Kg/m ³)	Elastic Ratio	Resilience
Gel #0	725990	21.4	880.379	0.910	1.105
Gel #1	668375	17.8	936.479	0.907	1.111
Gel #2	485176	6.8	923.468	0.901	1.114
Gel #3	386517	4.6	981.633	0.893	1.115
Gel #4	326166	3.3	834.336	0.849	1.120
Gel #5	210053	-	898.448	0.875	1.118

Acoustic Properties Data

Gelatin Type	Speed of Sound (m/s)	Acoustic Impedance	Acoustic Attenuation	
			α	η
Gel #0	1449.30 \pm 3.37	1.37 \pm 0.002	0.223 \pm 0.002	1.7 \pm 0.04
Gel #1	1465.20 \pm 4.19	1.37 \pm 0.003	0.202 \pm 0.017	1.681 \pm 0.025
Gel #2	1457.42 \pm 1.02	1.41 \pm 0.001	0.192 \pm 0.031	1.60 \pm 0.062
Gel #3	1458.85 \pm 3.87	1.25 \pm 0.001	0.158 \pm 0.005	1.679 \pm 0.115
Gel #4	1455.10 \pm 1.02	1.36 \pm 0.001	0.132 \pm 0.009	1.761 \pm 0.054
Gel #5	1466.00 \pm 1.68	1.64 \pm 0.001	0.132 \pm 0.023	1.737 \pm 0.056

